



# Intellect Pioneering Battery Technology Co.,Ltd.

## UN38.3 TEST REPORT AND DROP TEST

Product Category : Lithium-ion Polymer Rechargeable Battery

Model : IP461834

NO. : 20200135

Product Category : Lithium-Ion Polymer Rechargeable Battery      Model : H401604      NO. : 20200160											
TEST ITEM	TEST METHOD	CRITERION	CELL ID	Before The Test			After The Test			Test Results	Conclusion
				I.R(mΩ)	Voltage(V)	mass(g)	I.R(mΩ)	Voltage(V)	mass(g)		
T-1 Altitude Simulation	Test cell is stored at a pressure of 11.6kPa for above six hours at ambient temperature 20 ± 5 ℃.	No mass loss No leakage No venting No disassembly No rupture No fire.  The ocv of each test cell after testing is not less than 90%.	1#	176.54	4.172	5.24	176.55	4.170	5.23	No mass loss No leakage No venting No disassembly No rupture No fire	pass
T-2 Thermal Test	Test cell is stored for six hours at a test temperature equal to 72±2 ℃,followed by storage for six hours at a test temperature equal to -40±2 ℃.And the maximum time interval between test temperature extremes is 30 minutes.This procedure is to be repeated 10 times,after which all test cells are to be stored for 24 hours at ambienet temperature(20±5 ℃),and the total test time is at least one week.		2#	176.56	4.184	5.21	176.57	4.182	5.20		pass
			3#	176.58	4.189	5.25	176.59	4.187	5.24		pass
			4#	176.45	4.176	5.22	198.13	4.133	5.22		pass
			5#	176.47	4.174	5.28	198.42	4.128	5.27		pass
			6#	176.48	4.187	5.22	198.46	4.125	5.22		pass
			7#	176.57	4.182	5.29	198.35	4.129	5.28		pass
			8#	176.58	4.173	5.20	198.33	4.123	5.69		pass
T-3 Vibration	The vibration is a sinusoidal waveform with a logarithmic weep between 7 Hz and 200Hz and back to 7 Hz traversed in 15 minutes.This cycle is repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell.		9#	176.46	4.188	5.22	198.38	4.125	5.21		pass
			10#	176.31	4.176	5.25	176.32	4.175	5.24	pass	
			11#	176.35	4.184	5.26	176.35	4.182	5.26	pass	
T-4 Shock	Each cell is subjected to a half-sine shock of peak acceleration of 150gn and pulse duration of 6ms or to a half-sine shock of peak acceleration of 50gn and pulse duration of 11ms,and then it is subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell for a total of 18 shocks.		12#	176.38	4.184	5.23	176.39	4.183	5.22	pass	
			13#	176.42	4.172	5.27	176.43	4.170	5.26	pass	
			14#	176.45	4.178	5.29	176.45	4.177	5.28	pass	
			15#	176.48	4.189	5.22	176.49	4.187	5.21	pass	
			16#	176.49	4.177	5.28	176.50	4.175	5.27	pass	
			17#	176.53	4.176	5.22	176.54	4.175	5.21	pass	
			18#	176.90	4.182	5.26	176.91	4.180	5.25	pass	
			19#	176.83	4.183	5.22	176.84	4.182	5.21	pass	
T-5 External Short Circuit	The cell is subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at 57±4 ℃,this short circuit is continued for 1h after the cell external case temperature has returned to 57±4℃,and observe the cell for six hours.	20#	176.48	4.190	/	Max Temperature 55℃			No disassembly No fire	pass	
		21#	176.54	4.179	/	Max Temperature 55℃				pass	
		22#	176.56	4.182	/	Max Temperature 55℃				pass	
		23#	176.58	4.180	/	Max Temperature 55℃				pass	
T-6 Crush	1. A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1,5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. (a) The applied force reaches 13 kN ± 0,78 kN. (b) The voltage of the cell drops by at least 100 mV, (c) The cell is deformed by 50% or more of its original thickness./ 2. A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces.	If the external temperature don't exceed 170℃,there is no disassembly within six hours.	24#	103.59	3.857	/	Max Temperature 21℃			No disassembly No fire	pass
			25#	103.46	3.856	/	Max Temperature 22℃				pass
			26#	103.45	3.850	/	Max Temperature 21℃				pass
			27#	103.48	3.855	/	Max Temperature 21℃				pass
			28#	103.49	3.855	/	Max Temperature 21℃				pass
T-7 Overcharge	The cell is overcharge for 24 hours under the condition of twice max continuous charge current(1C) and twice max charge voltage(8.4V DC),and observe the cell for 7 days.	No disassembly No fire within 7 days	29#	176.42	4.177	/	/	/	/	No disassembly No fire within 7 days	pass
			30#	176.51	4.189	/	/	/	/		pass
			31#	176.58	4.198	/	/	/	/		pass
T-8 Forced Discharge	The cell is connected in series with a 12V D.C. power,and then is forced discharged with max discharge current,and observe the cell for 7 days.	No disassembly No fire within 7 days	32#	104.48	3.295	/	/	/	/	No disassembly No fire within 7 days	pass
			33#	103.45	3.297	/	/	/	/		pass
			34#	104.07	3.298	/	/	/	/		pass
Drop Test	Each package is capable of withstanding a 1.2m drop test in any orientation without damage to cells or batteries contained therein,without shifting of the contents so as to allow battery to battery contact and without release of contents.	No damage to batteries. No battery to battery contact. No release of congenets from the package.	35#	176.09	4.183	5.22	176.10	4.182	5.21	No damage to batteries. No battery to battery contact. No release of congenets from the package.	pass
			36#	176.98	4.184	5.22	176.99	4.183	5.21		pass
			37#	176.95	4.171	5.28	176.96	4.169	5.28		pass
			38#	176.04	4.177	5.24	176.05	4.176	5.23		pass
			39#	176.99	4.176	5.23	176.99	4.176	5.22		pass

Date of Test : 2016/02/25-2016/03/15

Operator: Hangeng Su

Checker: Ruiyuan Chen

Approval: Gui Xiao